

ProEXTENDERTM Topcoat

ProREZ Coatings, LLCP.O. Box 153, Cromwell, CT 06416-0153
877.511.3456 • www.prerezcoatings.com

TECHNICAL DATA SHEET

DESCRIPTION

ProExtender Topcoat is a non-reactive solvent to be used in the field to help lower viscosity, improve wetting, flow & leveling, as well as extend the overall working time of Polyaspartic ester especially in warmer application conditions. Compared to other, more aggressive solvents like Xylene or Methyl Acetate typically used with Polyaspartic, this material offers a more controlled evaporation rate, as well as a relatively sweet, mild ester odor. It is non-flammable, readily biodegradable, and non-corrosive.

PACKAGING

Available in 1 gallon cans.

DOSAGE

For best results, add 6-8 oz. by volume per gallon or 12-16 oz. by volume per 2 gallon mixed product.

ADVANTAGES

- ♦ Low volatile organic compound (VOC) content
- ♦ Mild to little odor
- ♦ Readily biodegradable
- ♦ Controlled evaporation rate for consistent "solvent power/effect"
- ♦ Viscosity reducer & excellent solvency for improved wetting, flow & leveling
- ♦ Reduces "orange peel" effect
- ♦ Improved-coating adhesion
- ♦ Non-flammable

PHYSICAL PROPERTIES

| | |
|-----------------------------|--------------|
| Appearance | Clear Liquid |
| Odor | Sweet |
| Weight/Gallon, lbs. @25°C | 8.97 |
| Flash Point, °C (P-M) | 225 |
| Viscosity @25°C, cps | 3.31 |
| Water Content, % wt. | <0.1 |
| Solubility in Water, % wt. | 4.3 |
| Vapor Pressure @25°C, torr. | 0.04 |
| Acid Content, mg KOH/g | <0.1 |

MIXING INSTRUCTIONS

Add the **ProExtender Topcoat** directly to the mixed ProSpartic or ProThane, and blend thoroughly.

DISPOSAL

Dispose in accordance with federal, state and local regulations.

TECHNICAL SUPPORT

For any application questions, please call **ProREZ** technical support at **877.511.3456**.

SDS

PLEASE SEE SAFETY DATA SHEET (SDS) FOR SAFETY AND PRECAUTIONS. USE PRODUCT AS DIRECTED. KEEP AT STORAGE TEMPERATURES BETWEEN 0°C - 40°C (32°F - 104°F). **KEEP OUT OF THE REACH OF CHILDREN.**

Warranties: Seller warrants that its goods, as described on the face hereof, are free from any defects in material or workmanship. Seller makes no other warranty, express or implied, and all implied warranties of merchantability and fitness for a particular purpose are hereby disclaimed. Seller shall not be liable for prospective profits or special indirect or consequential damages. Seller's sole liability and buyer's exclusive remedy for breach of any warranty as expressly limited, at seller's option, to replacement at the original F.O.B. point or refund of purchase price. Seller shall not be responsible for any claim resulting from failure to utilize product in the manner in which it was intended and in accordance with instruction provided for use of product. Any claim for breach of warranty shall be deemed waived unless buyer shall give seller written notice of such claim within sixty (60) days after delivery and shall allow seller reasonable opportunity to investigate claim and inspect product.