ProREZ™
Performance Resins and Coatings

Step Diagram

ProCryl CQ - MMA Single Broadcast - 40 or 25 mesh colored quartz aggregate



CONTRACTOR TESTED + APPROVED

*Note: Approximate thickness- variable with application method, size of aggregate, & substrate conditions.

ProREZ™
Performance Resins and Coatings

Step Diagram

ProCryl CQ - MMA Double Broadcast- 40 or 25 mesh colored quartz aggregate

ProCryl Prime Primer, Clear- (8-16 mils)

ProCryl Binder, Clear Base Coat1- Colored Quartz Broadcast - 1/16" (40 mesh)

ProCryl Binder, Clear Base Coat2 - Colored Quartz Broadcast - 1/16" (40 mesh)

ProCryl KT or UVR Top Coat, Clear - (16-18 mils)

Optional: 2nd ProCryl KT or UVR Top Coat, Clear - (10-16 mils)



Concrete Substrate

CONTRACTOR TESTED + APPROVED

*Note: Approximate thickness- variable with application method, size of aggregate, & substrate conditions.

ProREZ™
Performance Resins and Coatings

Step Diagram

ProCryl CQ-SL - MMA Broadcasted Slurry SL- 40 or 25 mesh colored quartz- 3/16”-1/4”

ProCryl Primer, Clear - (16 mils)

ProCryl Binder, Pigmented Slurry SL - (1/8”-3/16”)

ProCryl KT or UVR Clear Grout/Top Coat - (16-18 mils)

Optional: ProCryl KT or UVR Top Coat, Clear - (10-16 mils)



Concrete Substrate

CONTRACTOR TESTED + APPROVED

*Note: Approximate thickness- variable with application method, size of aggregate, & substrate conditions.